










Masstone	Tint	SG	% Pigment	Light Fastness	Alkali Fastness
 Yellow 2 G - 1 Cl. PY 74		1.20	40	7	5
 Yellow 2 G - 2 Cl. PY 1		1.15	40	7	5
 Yellow 2 G - 3 Cl. PY 83		1.15	40	6 - 7	5
 Oxyde Yellow 2 RN - 1 Cl. PY 42		1.80	60	8	5
 Red 4 Y - 2 Cl. PR 112		1.15	40	7	5
 Oxyde Red BN - 1 Cl. PR 101		1.95	50	8	5

High Durability, for exterior application

 HD Yellow 2 G - 154 Cl. PY 154		1.15	30	8	5
 HD Yellow 2 G - 184 Cl. PY 184		1.90	60	8	4 - 5

Masstone	Tint	SG	% Pigment	Light Fastness	Alkali Fastness
 Orange 3 R Cl. PO 13		1.15	40	4 - 5	4
 Violet 5 B Cl. PV 23		1.15	30	7 - 8	5
 Blue 7 G Cl. PB 15:0		1.15	32	8	5
 Blue 7 R Cl. PB 15:3		1.18	45	8	5
 Green 6 B Cl. PG 7		1.18	55	8	5
 Black 9 Y Cl. PBk 7		1.05	30	8	5

High Durability, for exterior application

 HD Orange O - 73 Cl. PO 73		1.10	38	8	4 - 5
 HD Red 4 Y - 254 Cl. PR 254		1.15	34	8	4 - 5